

TECHNICAL DATA SHEET

High Temperature Solid Silicone Rubber - Mouldings & Extrusions

Grades: SE50THT SE60THT & SE70THT

Temperature Range: -60°C (-76°F) to 270°C (518°F)

AVAILABILITY

The SE range of Silicone Rubbers is available in the form of mouldings and profile extrusions, which can be jointed or self-adhesive backed. They are particularly suited to use in oven door seals and gaskets, and are suitable for use in the food and beverage industry. There is a full range of standard colours available, and Silicone Engineering has the capability to colour match to customer requirements.

SPECIFICATIONS

White, Blue and Red Iron Oxide variants contain only ingredients that are listed by the American Food and Drugs Administration (FDA) under the 21 CFR number 177-2600.

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability tests.

GENERAL CHARACTERISTICS FOR SILICONE RUBBER

Brittle Point	-80°C (-112 °F)	ASTM D746
Limiting Oxygen Index	24.0 %	BS 2872 Part 1
Thermal Conductivity	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	
Dielectric Strength	23 kV.mm ⁻¹	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor @ 50c/s	3x10 ⁻⁴	VDE 0303
Volume Resistivity	3x10 ¹⁵ Ω.cm	VDE 0303

Environmental Resistance – Silicone rubber products have an excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general.

Other grades of silicone rubber available from Silicone Engineering are:

- * General Purpose Grades
- * Cellular silicone Products
- * High Temperature Grades
- * High Tear Grades
- * Flame Retardant Grades
- * Low Combustion Hazard Grades
- * Custom Compounds

This wide range of grades and production capability in silicone rubber is only available from



Greenbank Business Park, Blakewater Road, Blackburn, Lancashire, BB1 3HU England
Telephone: +44(0)1254 261321 Facsimile:+44(0)1254 583519 Web: www.silicone.co.uk

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

MECHANICAL PROPERTIES

Property	Units	SE50THT		SE60THT		SE70THT		Test Method
		Specification Limits	Typical Value	Specification Limits	Typical Value	Specification Limits	Typical Value	
Hardness	Shore A	50 ±5	50	60 ±5	60	70 ±5	70	ASTM D2240 DIN 53505
Tensile Strength	MPa	6.0 min.	8.8	6.0 min.	8.3	6.0 min.	8.6	BSISO 37 DIN 53504 die S1 ASTM D412 die C
	psi	870 min.	1276	870 min.	1204	870 min.	1247	
Elongation to Failure	%	250 min.	364	250 min.	393	250 min.	355	BSISO 37 DIN 53504 die S1 ASTM D412 die C
Tear Strength	N/mm	10.0 min.	15.9	12.5 min.	17.8	12.5 min.	17.5	BSISO 34-1 method C ASTM D624 die C
	lb/in	57.1 min.	108.5	71.4 min.	125.6	71.4 min.	124.5	
Compression Set 24 hours @ 150°C	%	35 max.	15	35 max.	15	35 max.	15	BS 903 pt A6 type B DIN 53517 type II ASTM D395 method B type 2
		35 max.	16	35 max.	15	35 max.	14	

*other information regarding the physical properties of these materials is available on request