

TECHNICAL DATA SHEET

Flame Retardant Solid Silicone Rubber - Sheeting

Grades: KSil40FR KSil50FR KSil60FR KSil70FR

Temperature Range: -60°C (-76°F) to 230°C (446°F)

AVAILABILITY

The K-SIL range of Silicone Rubbers has been specifically designed to produce silicone sheeting and can be purchased with self-adhesive backing. This range is particularly suited for use as seals and gaskets, in areas where public safety is critical. There is a full range of standard colours available, and Silicone Engineering has the capability to colour match to customer requirements.

Other materials available at silicone engineering include solid sheeting, sponge sheeting, sponge extrusion, customer compounding and cable grades

SPECIFICATIONS

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(i), (a)(1)(ii) vertical and (a)(1)(iv), (a)(1)(v) horizontal flammability tests.

They also meet the requirements of UL94 V0, V1, and V2. However, these materials do not hold UL approval.

GENERAL CHARACTERISTICS FOR SILICONE RUBBER

Brittle Point	-80°C (-112 °F)	ASTM D746
Limiting Oxygen Index	24.0 %	BS 2872 Part 1
Thermal Conductivity	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	
Dielectric Strength	23 kV.mm ⁻¹	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor @ 50c/s	3x10 ⁻⁴	VDE 0303
Volume Resistivity	3x10 ¹⁵ Ω.cm	VDE 0303

Environmental Resistance – Silicone rubber products have an excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general. Typical radiation resistance is > 10⁵ grays (>10⁷ rads)

Other grades of silicone rubber available from Silicone Engineering are:

- * General Purpose Grades
- * Cellular silicone Products
- * High Temperature Grades
- * High Tear Grades
- * Flame Retardant Grades
- * Low Combustion Hazard Grades
- * Custom Compounds

This wide range of grades and production capability in silicone rubber is only available from



Greenbank Business Park, Blakewater Road, Blackburn, Lancashire, BB1 3HU England
Telephone: +44(0)1254 261321 Facsimile:+44(0)1254 583519 Web: www.silicone.co.uk

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

MECHANICAL PROPERTIES

Property	Units	KSi40FR		KSi50FR		KSi60FR		KSi70FR		Test Method
		Specification Limits	Typical Value	Specification Limits	Typical Value	Specification Limits	Typical Value	Specification Limits	Typical Value	
Hardness	Shore A	40 ±5	43	50 ±5	52	60 ±5	62	70 ±5	72	ASTM D2240 DIN 53505
Tensile Strength	MPa	4.0 min.	6.5	5.5 min.	7.5	5.5 min.	8.0	6.0 min.	9.1	BSISO 37 DIN 53504 die S1 ASTM D412 die C
	psi	580 min.	943	798 min.	1088	798 min.	1160	870 min.	1320	
Elongation to Failure	%	300 min.	450	250 min.	330	250 min.	300	200 min.	280	BSISO 37 DIN 53504 die S1 ASTM D412 die C
Tear Strength	N/mm	8.5 min.	12.0	10.0 min.	15.0	12.5 min.	15.0	12.5 min.	14.0	BSISO 34-1 Method C ASTM D624 die C
	lb/in	48.5 min.	85.6	57.1 min.	102.8	71.4 min.	102.8	71.4 min.	97.1	
Compression Set 24 hours @ 150°C	%	30 max.	25	30 max.	14	30 max.	10	30 max.	12	BS 903 pt A6 type B DIN 53517 type II
22 hours @ 300°F		30 max.	22	30 max.	12	30 max.	10	30 max.	11	ASTM D395 method B type 2

*other information regarding the physical properties of these materials is available on request