

TECHNICAL DATA SHEET

Tough Solid Silicone Rubber - Sheetting

Grade: KSIL50KT and KSIL60KT

Temperature Range: -60°C to 200°C

MECHANICAL PROPERTIES

Property	Units	KSIL 50 KT		KSIL 60 KT		Test Method
		Specification Limits	Typical Value	Specification Limits	Typical Value	
Hardness	Shore A	45 ±6	40	60 ±5	60	ASTM D2240
Tensile Strength	MPa	7.0 min	9.6	8.0 min	9.9	BS ISO 37
Elongation to Failure	%	600 min	805	550 min	643	BS ISO 37
Tear Strength	N/mm	20 min	40.8	20 min	41.5	BS ISO 34-1 Method C

The KT range of silicone rubbers have been developed to produce a silicone product with high strength, high elasticity, improved abrasion resistance and the ability to withstand puncture damage without catastrophic failure. It is particularly suited for use as a vacuum bagging material. There is a full range of standard colours available, including translucent, and Silicone Engineering has the capability to colour match to customer requirements.

Other grades of silicone rubber available from Silicone Engineering are:

- * General Purpose Grades * Cellular silicone Products * High Temperature Grades * High Tear Grades *
- * Flame Retardant Grades * Low Combustion Hazard Grades * Custom Compounds

This wide range of grades and production capability in silicone rubber is only available from



Greenbank Business Park, Blakewater Road, Blackburn, Lancashire, BB1 3HU England
Telephone: +44(0)1254 261321 Facsimile: +44(0)1254 583519 Web: www.silicone.co.uk

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.